

SILPRO

MASCO™ MESH REINFORCING ALKALI RESISTANT MESH

High Performance

Reinforcing Mesh

Alkali Resistant

SILPRO LLC / 2 NEW ENGLAND WAY / AYER, MA 01432-1514 / 800-343-1501 / 978-772-4444 / FAX 978-772-7456 / WWW.SILPRO.COM

Silpro Masco™ Mesh is a high performance, alkali resistant, fiberglass reinforcing mesh for use in the **Silpro Masco™ Mesh System**. When used in conjunction with **Silpro's** polymer modified underlayments, **Masco™ Mesh** can be used to bridge cracks, stabilize punky and unsound substrates, and solidify and strengthen cinder ash screed construction

TECHNICAL DATA

Construction ASTM D-3775	Warp 6.0 in Weft 6.0 in
Weight	4.5 ounces per square yard
Weave	Leno
Finish	Alkali Resistant
Thickness ASTM D-1777	0.018 per inch
Minimum Tensile ASTM D-5035	Warp 150 lb/in Weft 210 lb/in

ADVANTAGES

- Alkali Resistant
- Highly Durable
- Commercial Grade Construction
- Resists Substrate Cracking
- Stabilizes Cinder Screed Substrates
- Strengthens Unsound and Punky Substrates

SURFACE PREPARATION

Follow instructions for surface preparation on **Silpro Masco™ Mesh System** data sheet

APPLICATION

Embed a layer of **Masco™ Mesh** into the wet **Masco™**. Overlap all mesh at least 2". With a trowel,

APPLICATION CONTINUED

starting in the middle and working towards the edges, force the mesh into the **Masco™**. Top off with a 1/8" layer of **Masco™** to fully embed the mesh. Allow minimum of 12 hours to dry. Minimum thickness of the finished mesh coat should be 1/4".

Note: **Silpro's** **Fasco™** or **Mascrete®** may be used in place of **Masco™** in certain applications. Consult **Silpro** for the best product choice for your application.

LIMITATIONS

- For interior applications only.
- Do not expose **Masco™ Mesh** to chemical attack.
- Substrate temperature must be 50° F. or above.
- For temperatures higher than 90° F. consult **Silpro's** Technical Service Dept.

PACKAGING

1 Roll is 38" wide by 150 ft long

COVERAGE

1 Roll covers approximately 475 square feet

GUARANTEE

Silpro LLC guarantees that their products are made of the finest raw materials under exacting care to produce products of the highest quality and will perform as stated when used in accordance with the manufacturer's printed instructions. Improper mixing, incorrect application or other factors beyond the control of the manufacturer may produce unsatisfactory results and can not be held to be the manufacturer's responsibility. **Silpro** accepts no responsibility beyond the purchase price of the **Silpro** product used. For further product information on **Masco™ Mesh** consult your local dealer or call **Silpro LLC** at: 800-343-1501; 978-772-4444; FAX 978-772-7456.

